


**YG K-2 CARBIDE
END MILLS**

G9444 SERIES

FLAT SHANK
SEITLICHE MITNAHMEFLÄCHEN

**CARBIDE, 2 FLUTE SHORT LENGTH
VOLLHARTMETALL, 2 SCHNEIDEN KURZ**

- ▶ Odpowiednie do frezowania na sucho w podwyższonych temperaturach
- ▶ Frezy walcowo czołowe o wysokiej wydajności
- ▶ Konstrukcja z dwoma ostrzami do frezowania rowków



up to Ø2mm over Ø2mm

MG HM DIN 6527 2 $\approx 30^\circ$ DIN 6535HB P.1070

Unit : mm

EDP No.	Mill Diameter	Shank Diameter	Length of Cut	Overall Length
G9444020	2.0	6	3	50
G9444030	3.0	6	4	50
G9444035	3.5	6	4	50
G9444040	4.0	6	5	54
G9444045	4.5	6	5	54
G9444050	5.0	6	6	54
G9444060	6.0	6	7	54
G9444070	7.0	8	8	58
G9444080	8.0	8	9	58
G9444090	9.0	10	10	66
G9444100	10.0	10	11	66
G9444120	12.0	12	12	73
G9444140	14.0	14	14	75
G9444160	16.0	16	16	82
G9444180	18.0	18	18	84
G9444200	20.0	20	20	92

Mill Dia. Tolerance(mm)	Shank Dia. Tolerance
0~-0.03	h6

◎ : Excellent ○ : Good

Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Copper	Graphite	Cast Iron	Aluminum	Stainless Steels	Titanium	Inconel	Acrylic	CFRP
~HB225	HB225~325	HRc30~40	HRc40~45	HRc45~55	HRc55~70									
◎	◎	◎				○		○	○	○	○	○		

YG K-2 CARBIDE END MILLS

RECOMMENDED CUTTING CONDITIONS EMPFOHLENE SCHNEIDKONDITIONEN

HSS

CBN
END MILLS

i-Xmill
END MILLS

i-HS mill
END MILLS

X5070
END MILLS

4G MILL
END MILLS

X-SPEED
ROUGHER
END MILLS

X-POWER
END MILLS

JET-POWER
END MILLS

TN MILL
END MILLS

V7 Mill
END MILLS

ALU-POWER
END MILLS

CRX S
END MILLS

D-POWER
GRAPHITE
END MILLS

D-POWER
CFRP
END MILLS

ROUTERS

K-2 CARBIDE
END MILLS

GENERAL
CARBIDE
END MILLS

TANK-POWER
END MILLS

GENERAL
HSS
END MILLS


MILLING
CUTTERS

TECHNICAL
DATA


CARBIDE, 2 FLUTE VOLLHARTMETALL, 2 SCHNEIDEN

G9424, G9A68, G9444, G9527, G9445, G9452 SERIES

MATERIAL	NON-ALLOYED STEELS ALLOY STEELS TOOL STEELS				ALLOY STEELS, HEAT RESISTANT STEELS				STAINLESS STEELS			
HARDNESS	~ HRc 30				HRc 30 ~ HRc 45							
STRENGTH	~1000N/mm ²				1000~1500N/mm ²							
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
1.0	14300	105	45	0.004	8500	65	25	0.004	7150	50	20	0.003
1.5	9350	150	45	0.008	5550	85	25	0.008	5600	80	25	0.007
2.0	7850	160	50	0.010	5150	100	30	0.010	4300	80	25	0.009
3.0	6100	180	55	0.015	3800	120	35	0.016	3150	100	30	0.016
4.0	5150	255	65	0.025	3150	155	40	0.025	2650	130	35	0.025
5.0	4300	270	70	0.031	2550	160	40	0.031	2150	135	35	0.031
6.0	3800	300	70	0.039	2300	190	45	0.041	1950	155	35	0.040
8.0	2850	325	70	0.057	1700	170	45	0.050	1450	155	35	0.053
10.0	2200	280	70	0.064	1350	135	40	0.050	1150	135	35	0.059
12.0	1850	240	70	0.065	1150	110	45	0.048	950	110	35	0.058
14.0	1700	215	75	0.063	1050	100	45	0.048	850	100	35	0.059
16.0	1500	185	75	0.062	950	95	50	0.050	700	95	35	0.068
20.0	1150	145	70	0.063	700	70	45	0.050	550	70	35	0.064



MATERIAL	CAST IRON				ALUMINUM ALLOYS				COPPER. BRASS NON-FERROUS METALS			
HARDNESS												
STRENGTH												
DIAMETER	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz	RPM	FEED	Vc	fz
1.0	18700	205	60	0.005	44000	330	140	0.004	24700	200	80	0.004
1.5	12100	205	55	0.008	27500	385	130	0.007	20300	300	95	0.007
2.0	9350	220	60	0.012	22000	460	140	0.010	16500	340	105	0.010
3.0	6050	220	55	0.018	15400	460	145	0.015	11000	340	105	0.015
4.0	4600	220	60	0.024	11000	460	140	0.021	8800	340	110	0.019
5.0	3650	220	55	0.030	9150	460	145	0.025	6800	340	105	0.025
6.0	2950	255	55	0.043	7600	485	145	0.032	5700	375	105	0.033
8.0	2200	275	55	0.063	5700	485	145	0.043	4400	375	110	0.043
10.0	1850	285	60	0.077	4600	485	145	0.053	3400	375	105	0.055
12.0	1450	295	55	0.102	3750	485	140	0.065	2850	375	105	0.066
14.0	1300	310	55	0.119	3300	485	145	0.073	2400	375	105	0.078
16.0	1100	320	55	0.145	2850	485	145	0.085	2200	375	110	0.085
20.0	900	340	55	0.189	2200	485	140	0.110	1700	375	105	0.110



※ The FEED, in long & extra long types, should be reduced by around 50%

RPM = rev./min.
FEED = mm/min.
Vc = m/min.
fz = mm/t